

HTCP-450

High Temperature Seal/Repair Putty

One-Part, Ceramic and Black Iron Oxide-Filled Water Based-Paste

For Applications to 1/4" Thick

Repairs Cast Iron and Steel Parts to 1600 °F

HANDLING & CURING	
Type	Inorganic
Filler	Iron Oxide
Number Components	1
Specific Gravity, gms/cc	2.90
Viscosity, cP	Paste
Maximum Temperature, °F (°C)	1600 (871)
Air Set, hrs	2 – 4
Heat Cure, °F, hrs	200, 3
Color	Black
Storage Temperature, °F	40 - 90

General Information

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Shelf Life

This product has a six months minimum shelf life after date of manufacture, unless otherwise specified, in original, unopened containers.

Note

The data contained in this technical data sheet are furnished for information only. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein. INCURE will not be liable for any indirect, special, incidental or consequential loss or damage arising from this INCURE product, regardless of the legal theory asserted. INCURE recommends that each user adequately test its proposed use and application before repetitive use, using this data as a guide.