Litemask™ 8114VT



UV/Visible Light/LED Curable Protective Peel-able Temporary Clear Mask

PRODUCT DESCRIPTION

Incure Litemask™ 8114VT UV/Visible Light/LED curable mask is a 100% solids, high strength peel-able, high temperature mask used widely in the electronics and aerospace industry. Cures tack-free in seconds, it forms a tough yet soft peel-able mask for surface protection against chemical stains and burnt marks on metals, glass and ceramics. Contains no VOCs or acids, its ultra-clean formulation does not affect masked surfaces before cure and leaves no residue or contamination after removal. Incure 8114VT is ideal for protection of critical surfaces during manufacturing processes and product surface protection.

LINCLIBED DRODERTIES

UNCURED PROPERTIES						
Chemical Type	Urethane Acrylate Hybrid, 100% Solids, No Solvents					
Appearance	Single Component, Clear Transparent					
Density, g/ml	1.09	1.09 Refractive Index 1.48 @20°C				
Flash Point, °C	>93	>93 Toxicity Low (Refer to MSDS)				
Viscosity, cP	18,000 - 32,000 @20rpm			Spindle	6	
Other viscosities are a viscosity range requesthis product may be p Email us at: support@local distributor for mo	offering, b fee.	ASTM	D2556			

¹ Viscosity (cP) taken at 25°C - Call to enquiry for other viscosities.

CURED PROPERTIES

Shore Hardness, Durometer		D30 to D40	ASTM 2240	
Linear Shrinkage / Expansion (-ve)		1.88%	ASTM D2566	
Water Absorption at 24hrs		0.52%	² ISTM D570	
Tensile (PSI)	PC-PC / PC-SS	1,600 / 100	ASTM 638	
* PC-PC / SS-SS / S-S / AL-AL * PC Substrate Failure	PC-S / PC-AL	1,300 / 1,000	ASTIVI 038	
Surface After Full Cure		Tack-Free	² ISTM D189	
Elongation at Break		26%	ASTM 638	
Thermal Range (Brittleness / Degrades) °C		-55 to 160	² ISTM D366	
Young's Modulus of Elasticity, MPa (PSI)		8 (1,200)	3 ASTM 638	
Linear CTE (α1 & α2), ppm/°C		α1=52 , α2=80	² ISTM D696	


² ISTM - refers to Incure Standard Test Method

RECOMMENDED UV CURE SCHEDULE (FULL CURE)

Full Cure Exposure Time			UVA	UVB	UVC	UVV
Fixture Time between g	glass slides	mW/cm ²	223	56	4	215
Exposure Time (s)	2.0	mJ/cm ²	446	112	8	430
F200P™ @3.75" Dist	5.0	mW/cm ²	223	56	4	215
Belt Speed (ft/min)	12.0	mJ/cm ²	1,115	280	19	1,075
F500™ @3.0" Dist	3.0	mW/cm ²	436	127	12	390
Belt Speed (ft/min)	8.0	mJ/cm ²	1,308	381	35	1,170
S20™ Spot (4-Pole LG) 0.4" Dist	mW/cm ²	3,000	530	50	3,400
Exposure Time (s)	1.0	mJ/cm ²	3,000	530	50	3,400
L9000™ LED Spot @ 0.67" Dist mV		mW/cm ²	2,800	42	12	102
Exposure Time (s)	3.0	mJ/cm ²	8,400	126	36	306

Cure times on 8mm ø adhesive sample. Belt speeds using C9000-F200Px1AB (Flood) and C9000-F500x1AC (Focused Beam) conveyors for area curing. Please consult IncureLab™ for any other requirements


TENSILE STRENGTH VS TEMPERATURE



UV INTENSITY REFERENCE TABLE

Incure UV Curing Lamp Model	⁴ Curing Distance vs UV Intensity					
Spot Curing (Diameter)	0.5" (12.6)	1" (25.4)	1.5" (38)	2" (50.8)	2.5" (63.5)	3" (76.2)
S20™ ARC (mW/cm²) / (ø mm)	1,400 (3)	1,500 (4)	650 (6)	360 (8)	240 (10)	175 (12)
L9000™ LED (mW/cm²) / (ø mm)	7,500 (9)	5,000 (10)	2,300 (17)	1,200 (20)	700 (25)	450 (30)
Flood/Focus Beam (Area)	UV Intensity (mW/cm²)					
F200™ ARC Flood (6" x 8")	325	280	245	215	190	165
F400™ ARC Flood (4" x 4")	860	570	440	345	270	215
F500™ ARC Focused (3" x 5")	1,040	685	530	415	325	260
L1044-365™ LED Flood (4" x 4")	2,675	2,380	1,900	1,625	1,430	1,280
L1044-405™ LED Flood (4" x 4")	2,950	2,625	2,150	1,900	1,650	1,450

⁴ Curing Distance is defined by the tip of light-guide or base of lamp housing to the bond area. All values are nominal with ±10% , with LED Flood Static Uniformity at ±78% and Dynamic Uniformity at ±90%. Recommended curing parameters in grey



SECONDARY HEAT CURE (Not Applicable)

Continuous Oven Bake	Duration
95°C (203°F)	120 mins
110°C (230°F)	60 mins
125°C (257°F)	30 mins

UV CURING SCHEDULE FOR THIS PRODUCT

Wavength λ	UVA (320 - 400nm)	UVB (290-320nm)	UVC (290-220nm)	VUV (400-700nm)
Minimum Intensity	223 mW/cm ²	56 mW/cm ²	4 mW/cm ²	215 mW/cm ²
Total Energy Required	1,115 mJ/cm ²	280 mJ/cm ²	19 mJ/cm ²	1,075 mJ/cm ²

Note: This product has been thoroughly tested to cure with F200P™ UV Flood Lamp. Intensity wavelengths (shaded) are crucial for curing this product. All measurements are made with EIT UV PowerPuck II. If you are unable to fully cure this product for some reasons, pls email us for assistance with your curing information

SHELF-LIFE, STORAGE, USE AND HANDLING OF THIS PRODUCT

Shelf-Life of this unopened product is a minimum of ONE (1) year from date of manufacture. Avoid direct exposure of bottle to visible light at all times. Containers should remained covered when not in use. Product should be stored in a dark cool place of 10°C to 32°C. Transfer of product into other packages void all warranties. Users should ensure all bonding surfaces are free of grease, mold release, or any contaminants, as bonding performance will be compromised. All tests for cured bonds should be carried out at ambient temperature. For safe handling of this product, please read Material Safety Data-sheet (MSDS) prior to use. Organic solvents, such as IPA, may be used to wipe away uncured material from surfaces.

EtO and GAMMA STERILIZATION (Not Applicable for this Product)

All Incure medical products are formulated to subject to standard sterilization methods, such as EtO and Gamma Radiation of 25 to 50 kGrays (cumulative). Enhanced moisture and thermal resistance of this product show excellent adhesion and bonding strength after one cycle of steam auto-clave test. Depending on bond design and structure of the application, users should test specific assemblies after subjecting them to sterilisation. Consult Incure Support Team for assistance, if your devices are subjected to more than one sterilization cycles.

NOTE

The data contained in this document are furnished for information only. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein. INCURE will not be liable for any indirect, special, incidental or consequential loss or damage arising from this INCURE product, regardless of the legal theory asserted. INCURE recommends that each user adequately test its proposed use and application before repetitive use, using this data as a guide.

Incure, Inc. 1 Hartford Square, Box 16 West, Suite C-3, New Britain, CT 06052, USA Tel: (860) 748 2979

Incure Adhesives Manufacturing Pte Ltd 33 Ubi Avenue 3 #04-23, Vertex Tower B, Singapore 408868 Tel: (65) 6509 3670





³ ASTM 638 Young's Modulus test speed @5mm/min for rigid and semi-rigid materials, @50mm/min for non-rigid materials, unless otherwise specified.

Material Safety Data Sheet (MSDS)

Released On: Jan 26, 2016 Version: 8114VT-04



Product and Company Identification

Product Name Technical Data

Product Code 8114VT

DECLARATION: The information furnished here is to the best of our knowledge. INCURE Incorporation does not assume any liability whatsoever for the accuracy or completeness of information contained herein. Final determination of suitability of any material is the sole responsibility of the end-user. All materials may present unknown health hazards and should be used with caution. Although certain

hazards are described herein, we cannot quarantee that these are the only hazards that exists

Company / Supplier Name

Hartford Square, Box 16 West, Suite C-3 West Gate, Door 18, New Britain, CT 06052, USA

Incure Adhesives Manufacturing Pte Ltd 33 Ubi Avenue 3 #04-23, Vertex Tower B Singapore 408868

Tel: (65) 62702188

Emergency Contact Information: Product Category

Tel: (860) 748-2979

Urethane Acrylate Hybrid, 100% Solids, No Solvents

Section 2 - Hazards Identification

GHS Pictogram

Signal Word GHS07 Warning

GHS Hazard Phrases: H315 Causes skin irritation.

> H317 May cause an allergic skin reaction. H319 Causes serious eve irritation H335 May cause respiratory irritation.

H412 Harmful to aquatic life with long lasting effects.

GHS Precautionary Phrases: P271 Use in a well-ventilated area.

> P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

P102 Keep out of reach of children.

P262 Do not get in eyes, on skin or on clothing.

GHS Response Phrases: P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if

present and easy to do. Continue rinsing.

P333+P313 If skin irritation or rash occurs: Get medical advice/ attention.

Keep only in original container. P234

GHS Storage and Disposal Phrases: P501 Dispose of contents/ container in accordance with local regulations.

GHS Classification: Physical and Chemical Hazards Not Classified.

Human Health H315, H317, H319, H335

Environment H412

Section 3 - Materia	Composition /	Safety Data on Product
CAS No.	% Composition	Description

GHS Classification 30 - 50 Specialty Urethane Acrylate Oligomer Blend H315, H319, H335 Proprietary 5888-33-5 25 - 50 Isobornyl Acrylate H315, H319, H335 868-77-9 2-Hydroxyethyl Methacrylate 0 - 5 H315, H319, H335 79-10-7 N.A. Acrylic Acid H226, H302, H313, H314, H315, H319, H332, H335, H400

Proprietary 1 - 5 2680-03-7 0 - 5 N,N-Dimethylacrylamide H315, H319, H335 2235-00-9 0 - 5 1-Vinylhexahydro-2H-Azepin-2-one H315, H319, H335 Proprietary 0 - 5 Specialty Urethane Acrylate Oligomer Blend H315, H319, H335 Proprietary 5 - 10 Specialty Co-Monomer Blend H315, H319, H335 7631-86-9 Silicon Dioxide H315, H319, H335

After Inhalation: Provide ample fresh air. Provide artificial respiration, give oxygen if experience difficulties in breathing. Consult doctor if symptoms persists

After eye contact: Rinse eye for up to 15 minutes under running water. If symptoms persists, consult an eye doctor.

After skin contact: Immediately wash with water and soap thoroughly. Remove contaminated clothings

Seek medical attention and treatment.

Suitable Extinguishing Agents Water spray, dry chemical or carbon dioxide will be useful. Fight larger fires with water spray or alcohol resistant foam.

Mouth respiratory protective device (face mask) is necessary in the event of fire.

Unusual fire or Explosion Hazards Uncontrolled polymerization may occur at high temperatures due to explosions or rupture. Toxic fumes and irritating organic vapors may be present.

Section 6 - Accidental Release Measures

Person-related Safety Precautions Not Required

Measures for environmental protection: Inform respective authority in case of seepage into water course or sewage system. Do not allow to enter sewers or waterways. Measures for cleaning / collecting: Soak up with absorbent inert materials (sand, silica gel, sawdust). Dike area to prevent spreading. Dispose of as a chemical waste in

accordance with current local, state and federal regulations. Please refer to Section 8 prior to clean-up

Storage:

Section 7 - Handling and Storage

General protective and hygienic measures

Handling: Information for safe handling at

Keep away from heat and direct sunlight. Use product with good ventilation/exhaust.

Requirements to be met by storerooms

Avoid exposure to sunlight.

< 35°C (95°F)

Information about protection against explosions and fire

workplace

Information about storage in one common

Not required. Keep bottle cap / receptacle

No special measures required Maximum Storage Temperature

Section 8 - Exposure Controls and Personal Protection

Additional information about design of technical systems No additional data, please refer to Section 7

Components with limit values that require monitoring N.A.

Additional information

Product does not contain any relevant quantities of materials with critical values needing monitoring at workplace

Keep away from foodstuffs, beverages such as drinking water. Immediately remove all soiled and contaminated clothing. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin

Breathing equipment

Use respiratory filter device in case of brief exposure resulting in discomfort. For prolonged exposure, use respiratory protective device that is independent of circulating air.

Revision Product design by IncureLab™

Material Safety Data Sheet (MSDS)

Released On: Jan 26, 2016 (04) Reprinted On: Jul 16, 2019



Use protective impermeable gloves that are resistant to the product. Selection of glove material should consider penetration times, rates of diffusion and degradation.

Use tightly sealed googles for best protection in a poorly ventilated area. Protection of eyes

Section 9 - Physical and Chemical Properties

Fluid / According to Technical Data Sheet / Characteristics > 93°C (200°F) Change in condition beyond melting point Undetermined Auto-Igniting Does not self-ignite

Change in condition beyond boiling point 115°C (240°F) Danger of Explosion None

Section 10 - Stability and Reactivity

Thermal decomposition / conditions to be

Protection of hands

No decomposition if used according to specification

Incompatible materials Strong oxidizing and reducing agents. Strong acids and bases. Free radical initiators.

Dangerous reactions

Dangerous products of decompositions Some Oxides of following chemicals may be formed - Carbon, Nitrogen, Silicon, Phosphorous, Amines.

Additional Information Smoke and toxic fumes may evolve as a result of uncontrolled exothermic chemical reactions caused by large masses of materials

interacting with curing agents (peroxides, amines, etc) and / or exposure to UV light / sunlight.

Section 11 - Toxicological Information

Acute Toxicity - LD/LC50 values that are relevant for classification Oral LD50 Dermal LD50 Inhalative LD50/4hr 5888-33-5 Isobornyl acrylate > 5000 mg/kg (rabbit) >2000 mg/kg (rat) 24650-42-8 Photo-initiator >2000 mg/kg (rat)

Primary irritant effect on skin/eye Irritant to skin and mucous and membranes. Danger of severe eye injury.

Additional toxicological information Product shows following dangers according to internally approved calculation methods of preparations: Harmful, Irritant.

Section 12 - Ecological Information

Ecotoxical Effects: Aquatic Toxicity 24650-42-8 Photo-Initiator - EC50/48hr 26mg/L (daphnia)

5888-33-5 Isobornyl acrylate - EC50/48hr 0.9mg/L (daphnia)

Remarks Toxic for aquatic organisms

Water hazard class 3 (self-assessment) - extremely hazardous for water. Do not allow produce tot reach ground water, water course or sewage system, even in small quantities. Danger to drinking water if even extremely small quantities leak into the ground. Also poisonous for fish and plankton in water bodies

Section 13 - Disposal Considerations

General Notes:

Must not be disposed with household garbage and do not allow product to reach sewage system.

Disposal of Uncleaned Packagings Disposal must be made according to official regulations

Section 14 - Transport Information

DOT Regulations: Hazard Class:

Land Transport ADR/RID (cross-border)		Air Transport ICAO-TI	Air Transport ICAO-TI and IATA-DGR		Transport IMDG
ADR/RID Class	Not Restricted	ICAO/IATA Class	Not Restricted	IMDG Class	Not Restricted
Danger Code		Label		Label	
UN Number		UN Number		UN Number	
Packaging Group		Packaging Group		Packaging Group	
Label		Label		Label	
Description of Goods		Description of Goods		Marine Pollutant	

Section 15 - Regulatory Information

Section 355 (Extremely hazardous substances) None

Acrylic Acid (79-10-7) Section 313 (Specific toxic chemical listings) TSCA (Toxic Substances Control Act) All ingredients are listed

California Proposition 65 No California Proposition 65 listed chemicals are known to be present.

None Chemicals known to cause reproductive toxicity for females None Chemicals known to cause reproductive toxicity for males Chemicals known to cause developmental toxicity None

Cancerogenity Categories EPA - None , IARC - Acrylic Acid , NTP - None , TLV - Acrylic Acid , NIOSH-Ca - None , OSHA-Ca -

Product has been classified and marked in accordance with directives on hazardous materials Product related hazard information

Hazard Symbol Harmful - Dangerous for the environment

Hazard-determining components of labelling None

Risk phrases Harmful by inhalation. Irritating to eyes, respiratory system and skin. Taxi to aquatic organisms. Safety phrases Keep container in a well-ventilated place. Do not breath gas/fumes/vapor/spray. In cases of contact with eyes, rinse immediately with plenty of water and seek medical advice. Use appropriate container to avoid environmental contamination.

Section 16 - Other Information

Information provided is based on our best and present knowledge. This, however, shall not constitute a guarantee for any specific product features and shall not establish a legally said contractual relationship.

Department issuing MSDS

Contact

Incure Inc. / Incure Adhesives Manufacturing Pte Ltd support@uv-incure.com

Revision Product design by IncureLab™